

B432/E

ABS 树脂 / ABS Resin

B432/E 是一款通用型挤出级 ABS 树脂。具有刚性与韧性良好的平衡，其流变性能和优良的热稳定性，有利于薄板和厚板的挤出成型。

B432/E is a general-purpose extrusion-grade ABS resin, featuring a good balance of rigidity and toughness. Its rheological properties and excellent thermal stability are conducive to the extrusion molding of thin and thick sheets.

B432/E 广泛用于挤出和共挤板材，赋予产品良好的表面光洁度和高拉伸比等优良性能。该材料适用于制冷、卫生、汽车、包装和家具（型材）等多种应用领域。

B432/E is widely used in extrusion and co-extrusion sheet production, providing products with excellent surface smoothness and high stretch ratio and other superior properties. This material is applicable to various application fields such as refrigeration, hygiene, automobiles, packaging and furniture (profiles).

性能特点 Benefits

中高耐热 Medium-high heat resistance  
高拉伸比 High stretch ratio  
良好的表面光洁度 Good surface smoothness

应用领域 Applications

挤出/共挤板材 Extruded or Co-extruded Sheets  
型材 Profiles  
聚合物合金 Polymer Alloys

性能 Properties	测试方法 Test Method	测试条件 Test Condition	典型值 Nominal Value
物理性能 Physical Properties			
密度 Density	ISO 1183	23℃	1.04 g/cm <sup>3</sup>
熔体质量流动速率 Melt Mass-Flow Rate (MFR)	ISO 1133	220℃/10kg	5.5 g/10min
模塑收缩率 Molding Shrinkage	ISO 294/4	23℃	0.4-0.7%
机械性能 Mechanical Properties			
拉伸屈服强度 Tensile Strength at Yield	ISO 527	50 mm/min	48 MPa
拉伸断裂伸长率 Tensile Elongation at Break	ISO 527	50 mm/min	15%
拉伸模量 Tensile Modulus	ISO 527	1 mm/min	2300 MPa
弯曲强度 Flexural Strength	ISO 178	2 mm/min	75 MPa
弯曲模量 Flexural Modulus	ISO 178	2 mm/min	2300 MPa
悬臂梁缺口冲击强度 Izod Notched Impact Strength	ISO 180/1A	23℃, 5.5J	19 kJ/m <sup>2</sup>
热性能 Thermal Properties			
热变形温度 Heat Deformation Temperature	ISO 75-2/A	1.8 MPa	82 °C
维卡软化温度 Vicat Softening Temperature	ISO 306	50N, 50℃/h	102 °C

备注：数据为典型值，仅供参考，不作为品质指标及其他用途的保证。

The data are typical values for reference only and are not used as quality specifications or other purposes.

## 加工工艺参数推荐

### Recommended Processing Parameters

#### 挤出成型 Extrusion

如无排气，建议在 80°C 下的空气循环烘箱中预干燥 2-4 小时。

If no venting, pre-drying required at 80°C for 2-4 hours in an air circulating oven.

熔体温度 190-230°C

Melt temperature 190-230°C

**备注：**以上加工参数仅供参考，实际工艺参数应根据不同机型、模具以及产品设计等进行适当调整。

The above processing parameters are for reference only. Actual processing parameters should be adjusted appropriately according to different equipment, molds and products.

**声明：**本文本的数据与信息源自我们现在的认识与经验。如果将来有了新的认识和经验，不排除对本文本的信息与数据进行修改而不预先通知的可能。由于使用条件和适用法律可能因地因时而异，客户有责任确定本文件里的产品和产品信息是否适合客户使用，并确保自己的工作场地和处理产品的方式符合可适用的法律和其它政府法规。亿科化学对本文本信息不承担任何责任与义务，也未提供任何保证。在本文本中关于产品的可售性或某一特殊用途的可适用性的所有默示保证在此明确地予以排除。

The data and information in this text are based on our current knowledge and experience. If there are new understandings and experiences in the future, we reserve the right to modify the information and data in this text without prior notice. Since the conditions of use and applicable laws may vary by location and time, the customer is responsible for determining whether the products and product information in this document are suitable for the customer's use, and for ensuring that their workplace and the way they handle the products comply with applicable laws and other government regulations. Eastech Chemical does not assume any responsibility or obligation for the information in this text, nor does it provide any warranty. All implied warranties regarding the merchantability or fitness for a particular purpose of the products mentioned in this text are hereby expressly excluded.

与我联系 Follow us at:



①上海市东方路 1217 号陆家嘴金融服务广场 2 层 2C 室 2F/2C, 1217 Dongfang Road, Shanghai, China

②苏州工业园区兴浦路 200 号联东 U 谷双创中心 17A 17A, 200 Xingpu Road, Suzhou Industrial Park, China

③山东省东营市东营区化工产业园郝纯路 85 号 85 Haochun Road, Dongying, Shandong, China

④广州市天河区国际金融城金硕一路 11 号汉银广场 4207 室 4207, 11 Jinshuo No.1 Road, Guangzhou, China

